

## **TEST REPORT**

**CLIENT** NOX Corporation

TEST METHOD CONDUCTED

ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring



DESCRIPTION OF TEST SAMPLE					
IDENTIFICATION	Dryback LVT/LVP with 0.5mm				

## **TEST RESULTS**

5 MINUTE RATINGS 24 HOUR RATINGS
----------------------------------

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	1	0	0	1	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	1	0	0	1	0	0
5% Phenol	1	0	0	1	0	0
Gasoline	0	0	0	0	0	0
Sulfuric Acid	1	0	0	1	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

## **RATING KEY**

0 - No change (----)

1 - Slight change

2 - Moderate change

3 - Severe change

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

Lang atleny

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us